



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>6</sup> : <b>G03G 9/00, 13/20, B05D 1/32, 1/06</b></p>	<p><b>A1</b></p>	<p>(11) International Publication Number: <b>WO 98/24002</b> (43) International Publication Date: <b>4 June 1998 (04.06.98)</b></p>
<p>(21) International Application Number: <b>PCT/US97/21669</b> (22) International Filing Date: <b>24 November 1997 (24.11.97)</b> (30) Priority Data: <b>08/774,324</b>      <b>25 November 1996 (25.11.96)</b>      <b>US</b> (71) Applicant: <b>SPECIALTY TONER CORPORATION [US/US];</b> <b>19 Industrial Road, Fairfield, NJ 07004 (US).</b> (72) Inventors: <b>BHATTACHARYA, Romit; 9 Zeck Road, Morris</b> <b>Plains, NJ 07950 (US). PERROTTA, Giovanni; 12 Fox Hill</b> <b>Drive, Wayne, NJ 07470 (US). DESHPANDE, Achyut,</b> <b>B.; 113 Fairview Avenue, South Orange, NJ 07079 (US).</b> <b>BILANCIO, Paul, R.; 24 Michele Road, Oak Ridge, NJ</b> <b>07438 (US).</b> (74) Agents: <b>FANUCCI, Allan, A. et al.; Pennie &amp; Edmonds LLP,</b> <b>1155 Avenue of the Americas, New York, NY 10036 (US).</b></p>		<p>(81) Designated States: <b>AL, AM, AU, AZ, BA, BB, BG, BR, BY,</b> <b>CA, CN, CU, CZ, EE, GE, GH, HU, ID, IL, IS, JP, KG,</b> <b>KP, KR, KZ, LC, LK, LR, LT, LV, MD, MG, MK, MN,</b> <b>MX, NO, NZ, PL, RO, RU, SG, SI, SK, SL, TJ, TM, TR,</b> <b>TT, UA, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW,</b> <b>SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ,</b> <b>MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK,</b> <b>ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI</b> <b>patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE,</b> <b>SN, TD, TG).</b></p> <p><b>Published</b> <i>With international search report.</i></p>
<p>(54) Title: <b>METHOD FOR PROTECTING ELECTROSTATIC IMAGES USING AN AMPHIPATHIC TONER</b></p> <p>(57) Abstract</p> <p>A method of protecting an electrostatic image on a substrate, wherein, an electrostatic image is formed on the substrate, and protected by applying an amphipathic liquid toner on the electrostatic image by electrostatic means, and fixing the amphipathic liquid toner to form a protective layer. The amphipathic liquid toner includes a carrier fluid, an amphipathic, non-gel copolymer, and a charge control agent to provide an electrostatic charge. The carrier fluid is typically an electrically resistive hydrocarbon solvent, having an electrical resistivity of at least about 10<sup>9</sup> ohm/cm, a dielectric constant of less than about 3, and a boiling point from about 68 °C to about 250 °C. The amphipathic, non-gel copolymer, which is insoluble as a whole in the carrier fluid, has at least one polymer segment that is soluble in the carrier fluid and at least one polymer segment that is insoluble in the carrier fluid. The soluble polymer segment includes at least one monomer of an alkyl acrylate or alkyl methacrylate and, optionally, at least one vinyl aromatic monomer. The insoluble polymer segment includes at least one vinyl ester monomer or at least one vinyl ester monomer and at least one acrylic acid or methacrylic acid monomer.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**METHOD FOR PROTECTING ELECTROSTATIC IMAGES**  
**USING AN AMPHIPATHIC TONER**

The invention relates to a method of protecting an  
5 image, typically an electrostatic print, with an amphipathic  
toner that is applied to the image with an electrostatic  
charge in the same manner as used to produce the image. The  
amphipathic toner provides images with protection from fading  
on exposure to light and resistance to scratching and  
10 weather. Images protected or produced with the method of the  
invention can thus be used in situations where they will be  
exposed to bright light or weather without the use of prior  
art protective laminates.

15

**BACKGROUND OF THE INVENTION**

Use of liquid toners for electrostatography, i.e.,  
the production of a visible, permanent image from a latent  
image consisting of a pattern of electrostatic charges, is  
20 well known. Liquid toners are typically used to develop  
electrostatic images in imaging systems that incorporate  
features similar to those of dry toner based copier and  
printer systems. However, liquid toner particles are  
significantly smaller than dry toner particles, i.e.,  
25 typically less than about 3  $\mu\text{m}$ , and are capable of producing  
toned images having very high resolution. Therefore, liquid  
toners have a number of advantages over dry toners, including  
the production of sharper and better defined images, a higher  
degree of and more delicate gradations of contrast, and  
30 cleaner whites. Liquid toners can also provide for a more  
economical use of the toner, a faster developing cycle, and  
simpler, less expensive and more trouble-free developing  
equipment.

Liquid toners are generally used to produce an  
35 image by the selective deposition of a pigment on a substrate  
to form a visible pattern. Although liquid toners are  
typically used in liquid electrostatic developers for

electrostatic printers and copiers, they can also be used in ink-jet printers, as well as equipment for high-speed print-outs and reproductions of microfilms, facsimile printing, and instrument recordings. Images produced with  
5 liquid toners include pictures, including half-tone pictures, line pictures, and photographic reproductions, as well as symbols, digits, graphs, and letters, i.e., any image that can be produced on an analog or digital electrostatic copier or printer. In particular, liquid toners are increasingly  
10 used to produce signs, posters, and charts for seminars and corporate events and meetings, binder cover inserts, packaging, short-run labels, store window display graphics, and outdoor billboards.

Typically, liquid toners have two phases, a  
15 continuous phase of a liquid hydrocarbon solvent system and a dispersed phase of dispersed pigments. The liquid hydrocarbon system has a high electrical resistivity, i.e., greater than  $10^9$  ohm-cm. This high resistivity does not allow the electrostatic charges on the substrate, typically a copy  
20 sheet or an electrostatic or xeroprinting master, to bleed off before the image is formed, thus maintaining the desired degree of contrast.

The liquid hydrocarbons should evaporate quickly, so that a thin film will evaporate in a few seconds at a  
25 temperature below the char point of paper, and should dry fully, so that a liquid-free pigment film is deposited. The liquid hydrocarbon system should be nontoxic when the vapor is inhaled or when the liquid comes in contact with skin, substantially odor free, and physically and chemically inert  
30 with respect to the copy sheet. A low viscosity is desirable, since this allows the dispersed phase to migrate through the continuous phase as a result of an attraction to an electrostatically charged substrate, to form an image by coupling with a pattern of electrostatic charges on the  
35 substrate.

The continuous phase contains dissolved and suspended solids, including pigments, a fixative or fixing

agent, typically a thermoplastic resin having the ability to flow under heat to fuse the deposited material to the substrate surface, and increase the bond between the deposited material and the substrate. Dissolved and  
5 suspended solids also include a dispersant, typically a long chain organic compound, such as a synthetic polymer, having both oil soluble and polar groups, to aid in the dispersion of suspended particles, and a charge director, typically a metallic derivative of a fatty acid or resin acid. The  
10 charge director is absorbed by individual pigment particles, which causes the pigment particles to aggregate in the dispersed phase. The dispersion of the aggregates formed is stabilized by the dispersant by an entropic repulsion mechanism.

15           The charge director also acts as an ionic surfactant, which forms inverse micelles in low dielectric media, such as the liquid hydrocarbon solvent system, and produces an electrostatic charge on particles dispersed in the continuous phase. Although a number of mechanisms are  
20 believed to be involved in the spontaneous separation of charges between the dispersed particles and the micelles, the acid-base chemistry of the dispersed particles and the ionic surfactant micelles is believed to play a major role in the production of charged particles, so that a proton or cation  
25 exchange from the particles to the micelles occurs when negatively charged particles are produced, and from the micelles to the particles when positively charged particles are produced. In addition, an electrode may be used to induce an electrostatic charge in the toner particles prior  
30 to their application to a substrate. The charge on the particles can be selected by the appropriate choice of charge director.

U.S. Patent Nos. 3,753,760, 3,900,412, 3,990,980, and 3,991,226 to Kosel disclose a type of liquid toner that  
35 reduces the number of different types of solid materials dissolved or suspended in the hydrocarbon solvent system, and may be used alone or in combination with a conventional toner

as described above. The disclosed liquid toner comprises a solvent system, such as the one described above, and a complex amphipathic polymer, a polymer in which at least one part of the molecule is solvated by the continuous phase and  
5 at least one part is insoluble in the continuous phase. The complex amphipathic polymer includes at least two different polymeric moieties that act as a fixer and a dispersant, and may also include an additional moiety that provides color to the toner. As a result, the amphipathic polymer combines the  
10 fixing agent, the dispersing agent, and, optionally, the color agent in one complex molecule. This type of liquid toner is essentially a colloidal suspension, and may be referred to as a latex toner.

Electrographic and electrophotographic processes  
15 are well known, and are described by Steven P. Schmidt et al., Handbook of Imaging Materials, Chap. 6, 227-252 (1991). There are the numerous variations of these processes, all of which incorporate the same basic steps of creating an electrostatic image on a substrate, developing the image with  
20 charged, colored particles, i.e., toner, optionally transferring the resulting developed image to a secondary substrate, and fixing the image to the substrate.

The first basic step, the creation of an electrostatic image, can be accomplished by a variety of  
25 methods. In the electrophotographic process, the electrostatic image is formed by a discharge of a uniformly charged photoconductor. The discharge occurs when the uniformly charged photoconductor is exposed to light, which may be reflected from or transmitted through an image that is  
30 being copied, or be provided by a laser in a digital laser copier or printer. The exposure may be analog or digital, and the photoconductor may be single use or rechargeable and reimageable. Single use devices may be repeatedly charged and developed after a single exposure, but are permanently  
35 imaged by the exposure. With both the single use and rechargeable devices, the electrostatic image is created by corona charging a photoconductor, followed by image wise

exposure and photodischarge. The electrostatic image is then developed with liquid toner having either positively or negatively charged particles, and transferred electrostatically to plain paper. The photoconductor may  
5 then be cleaned, charged, and reimaged.

In one form of the electrostatic process, a photosensitive element is permanently imaged to form areas of differential conductivity. The electrostatic image is created by uniform electrostatic charging followed by  
10 differential discharge of the imaged element. The electrographic or xeroprinting elements or masters can be repeatedly charged and developed after a single imaging exposure.

In an alternative electrographic process,  
15 electrostatic images are created ionographically. The latent image is created on a dielectric medium, such as paper or film, which is capable of holding a charge, by applying a voltage to one or more members of an array of electronic writing styluses or nibs. The styluses or nibs are selected  
20 in a manner that will produce the desired image when ions are produced from the applied voltage, placing a charge, and forming the latent image on the dielectric medium.

However the electrostatic image is produced, the image is developed with toner particles that possess a charge  
25 opposite to that of the charged surface to which they are applied. With liquid toners, a flowing liquid ensures the availability of sufficient toner particles to develop the image. When the flowing liquid is brought into direct contact with the electrostatic image, the charge of the  
30 electrostatic image creates a field that causes the charged toner particles to move through the nonconductive continuous phase by electrophoresis. As the charged toner particles contact the latent electrostatic image, the charge of the image is neutralized by the oppositely charged toner  
35 particles, and a layer of pigment is deposited, forming a permanent image.

If a reimageable photoreceptor or an electrographic master is used, the developed image must be transferred to paper or other substrate. To transfer the image, the substrate is charged electrostatically with the polarity  
5 chosen to cause the toner particles to transfer to the substrate. The substrate is then brought in contact with the reimageable photoreceptor or an electrographic master to produce the final image on the desired substrate.

Finally, the toned image must be fixed to the  
10 substrate. For self-fixing toners, residual solvent is removed from the substrate by air-drying or heating. The evaporation of the solvent results in a toner film that is bonded to the paper. For heat fusible toners, thermoplastic polymers are incorporated in the toner particles. Heating  
15 removes any residual solvent and fixes the toner to the substrate.

For color images, four different liquid toners having different colored pigments are used individually in four separate passes through the developer. Color printers  
20 typically have four separate sources of toner, which are typically referred to as toner fountains, one for each of the colored toners, i.e., one for black and one for each of the primary colors used in color developing: magenta, cyan, and yellow. However, there are commercially available printers  
25 that include a fifth fountain for an additional toner. On each pass of the substrate through the developer, the latent image is formed in a manner such that only that part of the image that is of a particular color is deposited on any given pass. After the fourth pass, the four toners form a full  
30 color image.

Where the fully developed image is a poster, sign, window display, billboard, or other image that will be exposed to bright light and/or weather, the image must be protected from fading, scratching, and weathering. This is  
35 typically accomplished by applying a layer of a clear plastic laminate over the surface of the image. However, this process is costly and labor intensive, because the image must



first be removed from the printer or copier on which it is produced, and then transported to a second device that applies the laminate. Typically, this process involves passing the image and a thin layer of plastic between a pair  
5 of heated rollers, which press the laminate onto the surface of the image. This bonds the laminate to the surface of the image to form a protective layer. However, under some circumstances the laminate can delaminate and separate from the surface of the image.

10 Therefore, there is a need for a method of protecting developed electrostatic images that does not involve the prior art lamination process. The present invention provides such a method.

15

#### SUMMARY OF THE INVENTION

The present invention relates to a method for protecting electrostatic images on a substrate, which comprises electrostatically applying an amphipathic liquid  
20 toner over an electrostatic image on a substrate, and fixing the amphipathic liquid toner to form a protective layer on the electrostatic image on the substrate. The amphipathic liquid toner comprises an electrically resistive hydrocarbon solvent as a carrier fluid, having an electrical resistivity  
25 of at least about  $10^9$  ohm·cm, a dielectric constant of less than about 3, and a boiling point from about 68°C to about 250°C, an amphipathic, non-gel copolymer, which is insoluble as a whole in the carrier fluid, and a charge control agent to provide an electrostatic charge. The amphipathic, non-gel  
30 copolymer has at least one polymer segment that is soluble in the carrier fluid and at least one polymer segment that is insoluble in the carrier fluid. The soluble polymer segment comprises at least one alkyl acrylate or alkyl methacrylate monomer or at least one alkyl acrylate or alkyl methacrylate  
35 monomer and at least one vinyl aromatic monomer. The insoluble polymer segment comprises at least one vinyl ester

monomer or at least one vinyl ester monomer and at least one acrylic acid or methacrylic acid monomer.

Typically, the alkyl group in the soluble polymer segment contains from about 3 to about 20 carbon atoms, and 5 the insoluble polymer segment is a homopolymer of vinyl acetate or a copolymer of vinyl acetate and an alkyl acrylate or alkyl methacrylate having up to about 20 carbon atoms. When present, the vinyl aromatic monomer typically contains a six member aromatic ring, and has a total of from about 6 to 10 about 10 carbon atoms. Preferably, the vinyl aromatic monomer is vinyl toluene or styrene.

Preferably, the soluble polymer segment comprises butyl, isobutyl, tertiarybutyl, 2-ethylhexyl, octyl, isononyl, decyl, lauryl, dodecyl, or stearyl acrylate or 15 methacrylate monomers, and the insoluble segment is a homopolymer of vinyl acetate or a copolymer of vinyl acetate and lauryl methacrylate, stearyl methacrylate, n-butyl methacrylate, acrylic acid, or methacrylic acid. The preferred charge control agent is a metallic salt of 20 naphthenic, octylic, or stearic acid, incorporating Li, Ca, Ba, Zr, Mn, Co, Ni, Cu, Zn, Cd, Al or Pt.

Preferred amphipathic, non-gel copolymers include copolymers of from about 10 to about 40 parts lauryl methacrylate and from about 100 to about 200 parts vinyl 25 acetate; copolymers of from about 10 to about 50 parts stearyl methacrylate and from about 100 to about 200 parts vinyl acetate; copolymers of from about 5 to about 45 parts 2-ethyl hexylacrylate and from about 100 to about 200 parts vinyl acetate; copolymers of from about 200 to about 275 30 parts of a vinyl acrylic resin containing a vinyl aromatic compound, from about 2 to about 5 parts lauryl methacrylate, from about 5 to about 10 parts n-butyl methacrylate, from about 10 to about 20 parts methacrylic acid, and from about 10 to about 20 parts vinyl acetate; and copolymers of from 35 about 50 to about 75 parts of a vinyl acrylic resin containing a vinyl aromatic compound, from about 50 to about 75 parts lauryl methacrylate, from about 50 to about 75 parts

vinyl acetate, and from about 1 to about 5 parts methacrylic acid.

The protective layer may be formed and applied in the method of the invention in a single step. In the  
5 alternative, the electrostatic image may be formed on a first substrate, while the protective layer is formed on a second substrate. The protective layer is then transferred from the second substrate to the electrostatic image on the first  
10 substrate to form the protective layer. In either case, an electrostatic charge is formed over at least a part of the electrostatic image, and the charged part of the electrostatic image is contacted with the amphipathic liquid toner, such that the amphipathic polymers move through the carrier fluid by electrophoresis, and adhere to the charged  
15 part of the electrostatic image to form the protective layer.

The present invention also relates to an electrostatic image on a substrate, which is resistant to fading from exposure to light, scratching, and weathering. The electrostatic image comprises a protective layer covering  
20 the electrostatic image on the substrate, where the protective layer includes an amphipathic liquid toner comprising an amphipathic, non-gel copolymer, as described above.

25

#### BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 illustrates the application of a protective layer by the method of the invention, using an electrophotographic printer.

30

Fig. 2 illustrates the application of a protective layer by the method of the invention ionographically.

Fig. 3 illustrates a cross section of an  
35 electrostatic image, protected with the method of the invention.

### DETAILED DESCRIPTION OF THE INVENTION

As used herein, the terms "electrostatic image" and "electrostatic print" refer to any image, picture, half-tone picture, line picture, photographic reproduction, symbol, digit, graph, letter, sign, poster, chart, binder cover insert, packaging, short-run label, store window display graphic, outdoor billboard, or any other type of image produced with any electrostatic method, including electrostatography, electrostatic developers, xeroprinting, xerography, and any other electrographic or electrophotographic method.

The present invention is directed to a method of protecting an electrostatic image by applying an amphipathic toner to the surface of the electrostatic image, using the same electrostatic method that was used to form the electrostatic image. Amphipathic toners contain amphipathic polymeric materials that can be given a positive or negative charge, so that they can be applied to the electrostatic image using an electrostatic charge. Amphipathic toner compositions can be clear or colorless or can be tinted with dyes, pigments, fluorescent pigments, or with other materials that provide additional properties when exposed to ultraviolet (UV) light. When applied to an electrostatic print with the method of the invention, amphipathic toners replace the plastic laminates typically used to provide protection from fading and resistance to scratching and weather, so that the image can be used for outdoor billboards or other any other purpose where the image will be exposed to UV light or weather.

Amphipathic toners useful in the invention comprise a dispersion of an amphipathic, non-gel copolymer and a charge control agent in a continuous phase of an electrically resistive dispersion medium or carrier fluid, typically an aliphatic hydrocarbon solvent. The amphipathic, non-gel copolymer, which is insoluble as a whole in the continuous phase, comprises a homopolymer or copolymer segment that is

soluble in the solvent and a homopolymer or copolymer segment that is insoluble in the solvent. The solvent soluble polymer segment comprises as the main monomer component at least one alkyl acrylate or methacrylic acid or at least one  
5 alkyl acrylate or methacrylate monomer and, optionally, at least one vinyl aromatic monomer, i.e., an aromatic compound containing at least one vinyl group. The solvent insoluble polymer segment comprises a vinyl ester monomer or a vinyl ester monomer with methacrylate acid or acrylic acid as the  
10 main monomeric component.

The charge control agent is added to impart a charge to the gel-polymer, and enhances the electrostatic charge conductance of the copolymer, which aids the dispersion stability of the copolymer. The higher dispersion  
15 stability is a necessary condition for the further application of the copolymer.

The charge control agent must be capable of improving the dispersion stability of the copolymer. Preferred charge control agents include metallic salts of  
20 naphthenic, octylic, and stearic acids. Metallic salts incorporating metals such as Li, Ca, Ba, Zr, Mn, Co, Ni, Cu, Zn, Cd, Al and Pt are useful as charge control agents. Group II and IV metals of the Periodic Table as well as transition metals are preferred, and aluminum salts are most preferred.  
25 Charge control agents useful in the method of the invention include, but are not limited to ionic surfactants, metal soaps, alkylated aryl sulfonates, alkylated aryl sulfonates with excess calcium or barium carbonate, such as basic barium petronate, neutral barium petronate, calcium petronate,  
30 neutral barium dinonylnaphthalene sulfonate, basic barium dinonylnaphthalene sulfonate, neutral calcium dinonylnaphthalene sulfonate, basic calcium dinonylnaphthalene sulfonate, dodecyl benzene sulfonic acid sodium salt, polyisobutylene succinimides, soy lecithin,  
35 N-vinyl pyrrolidone polymers, sodium salts of phosphated mono- and diglycerides with saturated and unsaturated acid substituents, polymers AB diblock copolymers of

2-(N,N)dimethylaminoethyl methacrylate quarternized with methyl-p-toluenesulfonate, AB diblock copolymers of poly-2-ethylhexyl methacrylate, and divalent and trivalent metal carboxylates, such as aluminum tristearate, barium stearate, chromium stearate, magnesium octoate, calcium stearate, iron naphthenate, and zinc naphthenate.

Any electrically resistive aliphatic hydrocarbon having an electrical resistivity of at least about  $10^9$  ohm·cm, a dielectric constant no more than about 3, and a boiling point of from about 68°C to about 250°C may be utilized as the dispersion medium or carrier fluid that functions as the continuous phase. Electrically resistive aliphatic hydrocarbons useful in the invention include, but are not limited to hexane, octane, nonane, decane, undecane, and dodecane, as well as commercially available solvents such as ISOPAR® G, H, I, and M, produced by Exxon Chemical, Inc., which are mixtures of isoparaffinic hydrocarbons, having boiling points of from about 150°C to 200°C. Preferred solvents include ISOPAR G®, which has a boiling point range of about 155° to 176°C, a flash point of about 40°C, and C<sub>10</sub> and C<sub>11</sub> hydrocarbons as the predominant molecular constituents, and ISOPAR H®, which has a boiling point range of about 169° to 193°C, a flash point of about 49°C, and C<sub>11</sub> and C<sub>12</sub> hydrocarbons as the predominant molecular constituents.

The soluble polymer segment of the amphipathic, non-gel copolymer stabilizes the dispersion. Preferably, the soluble polymer segment comprises alkyl acrylate or methacrylate monomers or alkyl acrylate or methacrylate and vinyl aromatic monomers. The alkyl acrylate or methacrylate typically has 3 to 20, preferably 4 to 18 carbon atoms. Useful alkyl acrylates and methacrylates include, but are not limited to butyl, isobutyl, tertiarybutyl, 2-ethylhexyl, octyl, isononyl, decyl, lauryl, dodecyl, and stearyl acrylates and methacrylates. The vinyl aromatic compound typically includes a six member aromatic ring, and has 6 to

10 carbon atoms. Preferred, vinyl aromatics include vinyl toluene and styrene.

In general, the polymerization product of an alkyl acrylate or methacrylate has a relatively low glass transition point, and the polymerization product of a vinyl aromatic has a relatively high glass transition point. Accordingly, a copolymer comprising at least one alkyl acrylate or alkyl methacrylate monomer and at least one vinyl aromatic monomer, such as the soluble polymer segment of the amphipathic, non-gel copolymers useful in the present invention, will have an intermediate glass transition point and a hardness that falls between that of a poly-alkyl acrylate or methacrylate and that of a poly-vinyl aromatic.

The insoluble polymer segment of amphipathic, non-gel copolymers useful in the present invention is a polymer segment containing vinyl acetate as a main component. The insoluble polymer segment may be a homopolymer of vinyl acetate or a copolymer of vinyl acetate and one or more other vinyl monomers, including lauryl methacrylate, stearyl methacrylate, n-butyl methacrylate, acrylic acid, and methacrylic acid. The vinyl acetate content of the insoluble polymer segment is typically 1 to 90 percent by weight, preferably 3 to 85 percent by weight.

Typically, the alkyl methacrylate and acrylates contain 1 to 20 carbon atoms, preferably 1 to 18 carbon atoms. Preferred alkyl methacrylates include n-butyl methacrylate and lauryl methacrylate. The preferred acid is methacrylic acid.

Diacyl peroxides are typically employed as polymerization catalysts to form the amphipathic, non-gel polymers that are useful in the method of the invention. Preferred catalysts include benzoyl peroxide, lauryl peroxide and p-chlorobenzoyl peroxide.

The copolymer aliphatic hydrocarbon solvent used as the continuous phase may also be used as a reaction solvent in the preparation of the amphipathic, non-gel copolymer in a one stage process in which both the soluble and insoluble

segments of the final insoluble polymer are added into the reaction solvent at room temperature, and polymerization is allowed to take place at elevated temperature. Following polymerization, the amphipathic toner is ready for use in the method of the invention without any further processing steps.

The molecular weight of the amphipathic, non-gel copolymers used in the final product differ depending on the kind and combination of monomers used, but preferably the molecular weight ranges from about 5,000 to about 50,000, more preferably from about 8,000 to about 20,000.

The ratio of the amount of soluble polymer segment to that of the insoluble polymer segment differs depending on the combination of monomers used. Because there is substantially complete conversion of the monomers into polymer, the weight ratio of the soluble polymer and insoluble polymer segments is the same as that of the weight ratio of the monomers that make up each segment. Typically, the copolymer comprises from about 5 to about 95 percent of the soluble polymer segment, based on the total weight of copolymer used in the final product, preferably about 10 to about 90 weight percent, more preferably from about 14 to about 85 weight percent. Copolymers having amounts of insoluble polymer segment outside the preferred range produce particles that are larger than those desired for the method of the invention. Larger particles tend to agglomerate and separate from the hydrocarbon solvent to form a sticky lump. For copolymers having amounts of insoluble polymer segment within the preferred range, the particle size of the insoluble polymer segment is smaller, which improves the further application of the protective coating. The preferred particle size ranges from about 0.1  $\mu\text{m}$  to about 0.5  $\mu\text{m}$ .

As long as the amphipathic, non-gel copolymer contains both the soluble polymer segment and the insoluble polymer segment, the method of bonding those segments is not critical. However, a graft copolymer comprising the soluble polymer segment with the insoluble polymer segment is preferred.



The amphipathic toner described above and exemplified below can be applied to an electrostatic image to form a protective layer. Typically, the image is formed, and the protective layer is applied using an electrostatic method, such as those described above and illustrated in Figs. 1 and 2. Fig. 1 illustrates electrophotographic device 10 in which photoconductor 12 is uniformly charged by charging source 14. An electrostatic image 16 is formed by an analog or digital imagewise photodischarge of charge photoconductor 12. In an analog discharge, the light 18 used to cause the photodischarge is typically reflected from or transmitted through an image being copied. For a digital discharge, the light source is typically a laser, which may be used to digitally scan an image to produce a copy, or may be controlled by a computer to produce a computer created digital image. In either case, the electrostatic image 16 is developed by contacting the image 16 with liquid toner 20 from toner fountain 28, containing a pigment, which is typically black, magenta, cyan, or yellow for color prints. The toned image 22 is then transferred to a substrate 24, such as paper or film, by applying a charge to the substrate from charging source 26. The toned image is attracted to the charge on substrate 24, and forms a final electrostatic image 30. For a full color image, four passes through the electrostatic device 10 are required. On each pass only that part of the image that corresponds to a specific color, i.e., black, magenta, cyan, or yellow, is formed. The image is developed with the appropriately colored toner 20 and transferred to substrate 24. In the method of the invention, electrophotographic device 10 typically has a fifth toner fountain 28 for the amphipathic toner 20. The amphipathic toner 20, as described above, is typically clear or colorless, but can be tinted with dyes, pigments, fluorescent pigments, or with other materials that provide additional properties when exposed to ultraviolet (UV) light. The amphipathic toner 20 is applied by uniformly charging the photoconductor 12, and contacting the charged photoconductor

12 with the amphipathic toner 20 without discharging the photoconductor 12. This produces a toned image 16 that comprises a single, uniform layer of amphipathic toner, which is then transferred onto the surface of the image 30 on the substrate 24. This results in an image 30, resistant to fading, scratching, and weathering, comprising an image 30 on a substrate 24 and a protective layer 32 of amphipathic toner.

Fig. 2 illustrates an alternative electrographic process, in which an electrostatic image is produced ionographically on a dielectric substrate, e.g., paper or film. Dielectric substrate 50 from dielectric substrate source 52 receives an electrostatic charge from an array of electrostatic writing style or nibs 54, creating electrostatic image 56. As in Fig. 1, the electrostatic image is developed by contact with a liquid toner 58 of the appropriate color from fountain 60 to form a toned image 62. The protective layer is then applied by charging the image over at least the entire area of the toned image 62, and contacting the charged image with the amphipathic toner. The toned image 62 is then fixed to the paper by heat, which evaporates residual carrier fluid, and forming a fixed layer 64 of amphipathic polymer on the toned image 62.

Fig. 3 illustrates a cross-section of an electrostatic image on a substrate, protected with the method of the invention. The protected electrostatic image 70 comprises a substrate 72, such as paper or film, a layer of toner particles 74, which are fixed to the substrate 72, and form the electrostatic image, and a layer of amphipathic toner 76, which forms a protective layer over the electrostatic image, and provides protection from light, scratching, and weathering.

The following non-limiting examples are merely illustrative of the preferred embodiments of the present invention, and are not to be construed as limiting the invention, the scope of which is defined by the appended claims. In particular, the following examples illustrate

methods of producing the amphipathic, non-gel copolymer for use in the method of the invention. All references to "part" and "parts" are parts by weight.

5

EXAMPLE 1

Three hundred thirty five parts ISOPAR G were mixed with 140 parts vinyl acetate and 25 parts lauryl methacrylate. After adding 0.7 percent benzoyl peroxide, based on the weight of the monomer mixture, the reaction was  
10 heated and stirred. Refluxing of the reaction mixture began at around 90°C. After about two hours, the refluxing reaction mixture became milky white, as an emulsion formed, and, due to the exotherm of the reaction, the temperature increased rapidly to 130°C, where it was maintained for  
15 approximately 24 hours. One part charge control agent (aluminum stearate) and 0.1 part UV resistant agent (Tinuvin 130) were then added. After about an hour, the heating source was disconnected, the reaction product was allowed to cool, and a white emulsion having a non-volatile matter  
20 content of 30 wt percent was obtained. The emulsion can be used in the method of the invention as an amphipathic toner without further processing steps.

EXAMPLE 2

25

The procedure in accordance with Example 1 was followed, except that 25 parts lauryl methacrylate was replaced by 25 parts stearyl methacrylate monomer as the soluble polymer segment. The reaction mixture was refluxed for about one hour, and, on cooling, a white emulsion having  
30 extremely superior dispersion stability and a non-volatile content of 30 wt percent was obtained. The emulsion can be used in the method of the invention as an amphipathic toner without further processing steps.

35

EXAMPLE 3

The procedure in accordance with Example 1 was followed, except that 25 parts lauryl methacrylate was

replaced by 25 parts 2-ethyl hexylacrylate monomer as the soluble polymer segment. On cooling, a white emulsion having superior dispersion stability and a non-volatile matter content of 30 wt percent was obtained. The emulsion can be used in the method of the invention as an amphipathic toner without further processing steps.

#### EXAMPLE 4

Two hundred thirty one parts ISOPAR G was mixed with 258 parts vinyl aromatic containing vinyl acrylic resin. Ten parts vinyl acetate, 5 parts lauryl methacrylate, and 6 parts methacrylic acid were then added, and the reaction mixture was stirred at room temperature. Following the addition of 3.4 percent of benzoyl peroxide the reaction mixture was heated and stirred. After about two hours, the temperature of the reaction mixture reached about 90°C, at which point a milky white emulsion began to form. Due to the exotherm of the reaction, the temperature of the mixture eventually rose to about 120°C, where it was maintained for about 24 hours. The reaction mixture was then further charged with 8 parts n-butyl methacrylate and 1.0 percent benzoyl peroxide. After about 4 additional hours at high temperature, the milky copolymer product was mixed with 1 part aluminum stearate and 0.1 part Tinuvin 130, and allowed to cool after about 1 hour. A white emulsion having superior dispersion stability and a non-volatile matter content of 33 wt. percent was obtained. The emulsion can be used in the method of the invention as an amphipathic toner without further processing steps.

30

#### EXAMPLE 5

Two hundred ninety five parts ISOPAR G was mixed with 67 parts vinyl aromatic containing vinyl acrylic resin, 68 parts vinyl acetate, 68 parts lauryl methacrylate, and 3 parts methacrylic acid. The reaction mixture was stirred at room temperature, and 0.8 percent benzoyl peroxide monomer was added. The reaction mixture was stirred, and, after

about 2 hours, the temperature increased to about 90°C, at which point a milky white emulsion began to form. Due to the exotherm of the reaction, the reaction temperature rose to about 120°C, where it was maintained for about 24 hours. The  
5 reaction mixture was then charged with additional 0.8 percent benzoyl peroxide monomer, and, after an additional 4 hours at about 120°C, 1 part aluminum stearate and 0.1 part Tinuvin 130 were added. After about another hour at that temperature, the heating was cut off and the reaction was  
10 allowed to cool to room temperature. A white emulsion having superior dispersion stability and a non-volatile matter content of 33 wt. percent was obtained. The emulsion can be used in the method of the invention as an amphipathic toner without further processing steps.

15 Any of the amphipathic toners exemplified above may be applied to an electrostatic image by any electrostatic means for producing an electrostatic image from a liquid toner known in the art to form a protective layer that protects the electrostatic imaging from fading due to  
20 exposure to light, as well as from scratching and weathering.

While it is apparent that the invention disclosed herein is well calculated to fulfill the objects stated above, it will be appreciated that numerous modifications and embodiments may be devised by those skilled in the art.  
25 Therefore, it is intended that the appended claims cover all such modifications and embodiments as falling within the true spirit and scope of the present invention.

30

35

THE CLAIMS

We claim:

1. A method for protecting electrostatic images  
5 on a substrate, which comprises:  
electrostatically applying an amphipathic liquid  
toner over an electrostatic image on a substrate, said  
amphipathic liquid toner comprising:  
a carrier fluid of an electrically resistive  
10 hydrocarbon solvent, having an electrical resistivity of at  
least about  $10^9$  ohm·cm, a dielectric constant of less than  
about 3, and a boiling point from about 68°C to about 250°C,  
an amphipathic, non-gel copolymer, which is  
insoluble as a whole in the carrier fluid, said amphipathic,  
15 non-gel copolymer having at least one polymer segment that is  
soluble in the carrier fluid and at least one polymer segment  
that is insoluble in the carrier fluid, wherein the soluble  
polymer segment comprises at least one alkyl acrylate or  
alkyl methacrylate monomer or at least one alkyl acrylate or  
20 alkyl methacrylate monomer and at least one vinyl aromatic  
monomer; and wherein the insoluble polymer segment comprises  
at least one vinyl ester monomer or at least one vinyl ester  
monomer and at least one acrylic acid or methacrylic acid  
monomer, and  
25 at least one charge control agent to provide an  
electrostatic charge; and  
fixing the amphipathic liquid toner, forming a  
protective layer on the electrostatic image on the substrate.
- 30 2. The method of claim 1, wherein the alkyl group  
in the soluble polymer segment contains from about 3 to about  
20 carbon atoms, and the insoluble polymer segment is a  
homopolymer of vinyl acetate or a copolymer of vinyl acetate  
and an alkyl acrylate or alkyl methacrylate having up to  
35 about 20 carbon atoms.

3. The method of claim 2, wherein the soluble polymer segment comprises butyl, isobutyl, tertiarybutyl, 2-ethylhexyl, octyl, isononyl, decyl, lauryl, dodecyl, or stearyl acrylate or methacrylate monomers, and the insoluble 5 segment is a homopolymer of vinyl acetate or a copolymer of vinyl acetate and lauryl methacrylate, stearyl methacrylate, n-butyl methacrylate, acrylic acid, or methacrylic acid.

4. The method of claim 2, wherein the soluble 10 polymer segment comprises a vinyl aromatic monomer, which contains a six member aromatic ring, and has a total of from about 6 to about 10 carbon atoms.

5. The method of claim 4, wherein the vinyl 15 aromatic monomer is vinyl toluene or styrene.

6. The method of claim 1, wherein the charge control agent is a metallic salt of naphthenic, octylic, or stearic acid, incorporating Li, Ca, Ba, Zr, Mn, Co, Ni, Cu, 20 Zn, Cd, Al or Pt.

7. The method of claim 1, wherein the amphipathic, non-gel copolymer comprises from about 10 to about 40 parts lauryl methacrylate and from about 100 to 25 about 200 parts vinyl acetate.

8. The method of claim 1, wherein the amphipathic, non-gel copolymer comprises from about 10 to about 50 parts stearyl methacrylate and from about 100 to 30 about 200 parts vinyl acetate.

9. The method of claim 1, wherein the amphipathic, non-gel copolymer comprises from about 5 to about 45 parts 2-ethyl hexylacrylate and from about 100 to 35 about 200 parts vinyl acetate.

10. The method of claim 1, wherein the  
amphipathic, non-gel copolymer comprises from about 200 to  
about 275 parts of a vinyl acrylic resin containing a vinyl  
aromatic compound, from about 2 to about 5 parts lauryl  
5 methacrylate, from about 5 to about 10 parts n-butyl  
methacrylate, from about 10 to about 20 parts methacrylic  
acid, and from about 10 to about 20 parts vinyl acetate.

11. The method of claim 1, wherein the  
10 amphipathic, non-gel copolymer comprises from about 50 to  
about 75 parts of a vinyl acrylic resin containing a vinyl  
aromatic compound, from about 50 to about 75 parts lauryl  
methacrylate, from about 50 to about 75 parts vinyl acetate,  
and from about 1 to about 5 parts methacrylic acid.

15

12. The method of claim 1, further comprising  
forming and applying the protective layer in a single step.

13. The method of claim 1, further comprising  
20 forming the electrostatic image on a first substrate, forming  
the protective layer on a second substrate, and transferring  
the protective layer from the second substrate to the  
electrostatic image on the first substrate.

25 14. The method of claim 1, further comprising  
producing an electrostatic charge over at least a part of the  
electrostatic image, and contacting the charged part of the  
electrostatic image with the amphipathic liquid toner, such  
that the amphipathic polymers move through the carrier fluid  
30 by electrophoresis, and adhere to the charged part of the  
electrostatic image to form the protective layer.

15. An electrostatic image on a substrate,  
produced according to the method of claim 1.

35



16. An electrostatic image on a substrate, said image having resistance to fading from exposure to light, scratching, and weathering, comprising:

a protective layer covering the electrostatic image  
5 on the substrate, wherein the protective layer includes an amphipathic liquid toner comprising:

an amphipathic, non-gel copolymer, which is insoluble as a whole in a hydrocarbon solvent carrier fluid, having at least one polymer segment that is soluble in the  
10 carrier fluid and at least one polymer segment that is insoluble in the carrier fluid, wherein the soluble polymer segment comprises at least one alkyl acrylate or alkyl methacrylate monomer or at least one alkyl acrylate or alkyl methacrylate monomer and at least one vinyl aromatic monomer;  
15 and wherein the insoluble polymer segment comprises at least one vinyl ester monomer or at least one vinyl ester monomer and at least one acrylic acid or methacrylic acid monomer.

17. The electrostatic image of claim 16, wherein  
20 the alkyl group in the soluble polymer segment contains from about 3 to about 20 carbon atoms, and the insoluble polymer segment is a homopolymer of vinyl acetate or a copolymer of vinyl acetate and an alkyl acrylate or alkyl methacrylate having up to about 20 carbon atoms.

25

18. The electrostatic image of claim 17, wherein the soluble polymer segment is a copolymer of butyl, isobutyl, tertiarybutyl, 2-ethylhexyl, octyl, isononyl, decyl, lauryl, dodecyl, or stearyl acrylate or methacrylate  
30 and vinyl toluene or styrene, and the insoluble segment is a homopolymer of vinyl acetate or a copolymer of vinyl acetate and lauryl methacrylate, stearyl methacrylate, n-butyl methacrylate, acrylic acid, or methacrylic acid.

19. The electrostatic image of claim 17, wherein the soluble polymer segment further comprises vinyl toluene or styrene monomers.

20. The electrostatic image of claim 17, wherein the amphipathic, non-gel copolymer comprises from about 10 to about 40 parts lauryl methacrylate and from about 100 to about 200 parts vinyl acetate.

5

21. The electrostatic image of claim 17, wherein the amphipathic, non-gel copolymer comprises from about 10 to about 50 parts stearyl methacrylate and from about 100 to about 200 parts vinyl acetate.

10

22. The electrostatic image of claim 17, wherein the amphipathic, non-gel copolymer comprises from about 5 to about 45 parts 2-ethyl hexylacrylate and from about 100 to about 200 parts vinyl acetate.

15

23. The electrostatic image of claim 17, wherein the amphipathic, non-gel copolymer comprises from about 200 to about 275 parts of a vinyl acrylic resin containing a vinyl aromatic compound, from about 2 to about 5 parts lauryl methacrylate, from about 5 to about 10 parts n-butyl methacrylate, from about 10 to about 20 parts methacrylic acid, and from about 10 to about 20 parts vinyl acetate.

20

24. The electrostatic image of claim 17, wherein the amphipathic, non-gel copolymer comprises from about 50 to about 75 parts of a vinyl acrylic resin containing a vinyl aromatic compound, from about 50 to about 75 parts lauryl methacrylate, from about 50 to about 75 parts vinyl acetate, and from about 1 to about 5 parts methacrylic acid.

30

35




FIG. 1




FIG. 2




FIG. 3

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/US97/21669

**A. CLASSIFICATION OF SUBJECT MATTER**

IPC(6) :G03G 9/00, 13/20; B05D 1/32, 1/06

US CL :430/114, 124; 427/466, 468, 469

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

U.S. :

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched  
NONEElectronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
APS**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4,818,657 (KONDO et al) 04 April 1989, column 2, line 31, to column 4, line 39, and column 6, lines 38-49.	1-24
Y	US 4,259,429 (GILLIAMS et al.) 31 March 1981, Abstract, column 2, lines 1-17, and column 2, line 44, to column 3, line 28.	1-24
Y	US 3,669,859 (MERRILL) 13 June 1972, Abstract, column 3, lines 15-19 and 39-58, column 4, lines 8-18 and 66-75, column 5, lines 21-29.	1-24
Y	AU 257,190 (PHOTOSTATIC ENTERPRISES LIMITED) 02 May 1963, pages 12-15.	1-24
A	US 3,820,987 (WELLS et al.) 28 June 1974, Abstract and Examples.	1-24

☒ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* "A"	Special categories of cited documents: document defining the general state of the art which is not considered to be of particular relevance	"T"	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"B"	earlier document published on or after the international filing date	"X"	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L"	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y"	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O"	document referring to an oral disclosure, use, exhibition or other means	"A"	document member of the same patent family
"P"	document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

23 JANUARY 1998

Date of mailing of the international search report

02 MAR 1998

 Name and mailing address\* of the ISA/US  
 Commissioner of Patents and Trademarks  
 Box PCT  
 Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

SUSAN BERMAN

Telephone No. (703) 308-1235

**INTERNATIONAL SEARCH REPORT****International application No.**  
**PCT/US97/21669****C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT**

<b>Category*</b>	<b>Citation of document, with indication, where appropriate, of the relevant passages</b>	<b>Relevant to claim No.</b>
<b>A</b>	<b>US 3,861,911 (LUEBBE, JR.) 21 January 1975, Abstract, column 3, lines 42-53, and column 5, lines 1-22.</b>	<b>1-24</b>

**THIS PAGE BLANK (USPTO)**